

Topological phase in a two-dimensional metallic heavy-fermion system

Tsuneo Yoshida, Robert Peters, Satoshi Fujimoto, and Norio Kawakami

Department of Physics, Kyoto University, Kyoto 606-8502, Japan

(Dated: January 25, 2013)

We report on a topological insulating state in a heavy-fermion system away from half-filling, which is hidden within a ferromagnetic metallic phase. In this phase, the cooperation of the RKKY interaction and the Kondo effect, together with the spin-orbit coupling, induces a spin-selective gap, bringing about topologically non-trivial properties. This topological phase is robust against a change in the chemical potential in a much wider range than the gap size. We analyze these remarkable properties by using dynamical mean field theory and the numerical renormalization group. Its topological properties support a gapless chiral edge mode, which exhibits a non-Tomonaga-Luttinger liquid behavior due to the coupling with bulk ferromagnetic spin fluctuations. We also propose that the effects of the spin fluctuations on the edge mode can be detected via the NMR relaxation time measurement.

PACS numbers: 73.43.-f, 71.10.-w, 71.70.Ej, 71.10.Fd

Introduction- In this decade, $\mathbb{Z}_2$ topological band insulators (TBIs) have been found as new classes of quantum phases.^{1,2} Their topological order is described in terms of the corresponding topological invariant and reflected in the existence of gapless edge modes which are protected by time-reversal symmetry. Such phases have been experimentally found in HgTe/CdTe quantum wells³ and bismuth based compounds.⁴⁻⁶ These discoveries have stimulated the study of topologically non-trivial phases, providing a new research arena in condensed matter physics. One of the current major issues is the influence of strong correlations upon these topological phases, because electron correlations under such non-trivial conditions are expected to spark new and exotic phenomena. This issue has further been stimulated by theoretical proposals for the realization of topological phases in d - and f -electron systems⁷⁻¹¹, triggering theoretical studies on the competition between topological phases and long-range ordered phases¹²⁻²¹ and topologically non-trivial phases induced by the Coulomb interaction²²⁻²⁴.

Heavy-fermion systems, which are representative examples for strongly correlated systems, have exhibited various intriguing properties due to the competition of the RKKY interaction and the Kondo effect, such as huge enhancement of the effective mass, metamagnetism, orbital order, unconventional superconductivity near the critical point, etc. A recent remarkable proposal in heavy-fermion systems is a *topological Kondo insulator*, first, discussed by Dzero *et al.*²⁹ Its properties have been further studied in ref.^{30,31}, and the first-principle

calculations have predicted that the filled skutterudites CeOs₄As₁₂¹¹ and SmB₆³²⁻³⁵ can be strong topological Kondo insulators.

All the above topological insulators have been proposed, of course, for the insulating phases. We now ask the question: *Is it possible to realize a topologically non-trivial phase within a metallic phase away from a commensurate filling?* Naively, it seems to be impossible to find a topological insulator, if the noninteracting system is metallic. However, we will demonstrate that it is possible to find a topological insulating state even within a metallic phase, if strong electron correlations are present.

In this paper, we propose a spin-selective topological insulator in a two-dimensional heavy-fermion system, which is hidden within a ferromagnetic metallic phase. For the stabilization of this phase, the RKKY interaction and the Kondo effect, together with the spin-orbit coupling, play the principal role. Furthermore, these effects support the robustness of this topological phase against a shift of the chemical potential, which is much larger than the gap size. The topologically non-trivial structure gives rise to a chiral gapless mode at the boundaries. With a phenomenological treatment, we clarify that this gapless mode shows a non-Tomonaga-Luttinger behavior due to the coupling to bulk magnetic fluctuations.

Model and method- To study the topological properties of two-dimensional heavy-fermion systems, we employ the periodic Anderson model with the spin-orbit coupling, which is an extension of the Bernvig-Hughes-Zhang model³⁶. The corresponding Hamiltonian reads

$$H = \sum_{i,\alpha,\sigma} \varepsilon_{\alpha} n_{i,\alpha,\sigma} - \sum_{i,j,\sigma} \hat{c}_{i,\alpha,\sigma}^{\dagger} \hat{t}_{i,j,\sigma,\alpha,\alpha'} \hat{c}_{j,\alpha',\sigma} + U \sum_i n_{i,f,\uparrow} n_{i,f,\downarrow}, \quad (1)$$

$$-\hat{t}_{i,j,\sigma} = \begin{pmatrix} -t_{ff}(\delta_{i,j+\hat{x}} + \delta_{i,j+\hat{y}}) & t_{cf}(-\text{sign}(\sigma)(\delta_{i,j+\hat{y}} - \delta_{i,j-\hat{y}}) + i(\delta_{i,j+\hat{x}} - \delta_{i,j-\hat{x}})) \\ t_{cf}(\text{sign}(\sigma)(\delta_{i,j+\hat{y}} - \delta_{i,j-\hat{y}}) + i(\delta_{i,j+\hat{x}} - \delta_{i,j-\hat{x}})) & t_{cc}(\delta_{i,j+\hat{x}} + \delta_{i,j+\hat{y}}) \end{pmatrix},$$

where $n_{i,\alpha,\sigma} = c_{i,\alpha,\sigma}^{\dagger} c_{i,\alpha,\sigma}$. The operator $c_{i,\alpha,\sigma}^{\dagger} (c_{i,\alpha,\sigma})$ creates (annihilates) an electron at site i and in orbital

$\alpha = c, f$ and spin $\sigma = \uparrow, \downarrow$ state. The hopping integral t_{ff} is assumed to be much smaller than t_{cc} in order to describe a heavy-fermion system. The hybridization term, which is labeled by t_{cf} between c - and f -electrons, has the specific form characteristic of the spin-orbit coupling,³⁶ and can drive the system into a topologically non-trivial band insulator. We analyze the system by using dynamical mean field theory (DMFT)^{37–39}, which treats local correlations exactly by mapping the original lattice model onto an effective impurity model. We employ the numerical renormalization group (NRG) method to solve the impurity model.^{40,41} In this study we set the model parameters as $t_{ff} = 0.2t_{cc}$, $t_{cf} = t_{cc}$, $\epsilon_c = 0$, and $\epsilon_f = -8t_{cc}$. The hopping integral t_{cc} is chosen as the energy unit.

Bulk Properties- Let us start with the half-filled case,³¹ where each lattice site is occupied by one conduction electron in average ($N_{tot} = 2$). The DMFT results are summarized in the phase diagram (Fig. 1). At half filling, we can observe the competition between the RKKY interaction and the Kondo effect. Namely, in the strong coupling region ($U > 12$), the RKKY interaction is dominant and the system shows a topologically trivial antiferromagnetic order. When the interaction is decreased, the Kondo effect becomes dominant, and the system enters the Kondo insulating phase for $U < 12$, where the Kondo gap is formed. Note that for $4.8 < U < 12$, this Kondo insulator has non-trivial topological properties, which can be detected via the spin Chern number. This "topological Kondo insulator" is essentially identical to those proposed previously,^{29–31} although the models studied there are slightly different from the present one.




FIG. 1: (Color Online). Zero-temperature phase diagram as functions of interaction strength U and total filling N_{tot} , obtained by the DMFT+NRG method. The colors represent the magnitude of magnetic moments of f -electrons for each phase. For $N_{tot} \lesssim 1.6$, a ferromagnetic phase is realized. In the region enclosed by two white lines, a spin-selective topological Kondo insulator (SSTKI) is realized; the majority-spin state forms a bulk gap which induces non-trivial properties.

The antiferromagnetic order immediately vanishes when the system is doped, and it enters a paramagnetic

metallic phase for $1.6 \lesssim N_{tot} \lesssim 1.9$, as shown in Fig. 1. Upon further doping, the system shows a ferromagnetic order for $N_{tot} \lesssim 1.6$. These properties can be naturally expected for ordinary Kondo lattice systems. The remarkable point is that a "topological insulator" is hidden within this ferromagnetic metallic phase. To confirm the existence of the gap, we plot the spin-dependent local density of states (LDOS) for several values of interaction strength in Fig. 2. In this figure, we assume that the majority electrons are up-spin electrons ($N_{\uparrow} < N_{\downarrow}$, where $N_{\sigma} = \langle n_{c,\sigma} + n_{f,\sigma} \rangle$). At $U = 12$, where the system is in the Kondo regime, the f -electrons are weakly magnetized, and no gap is observed, as seen in Fig. 2. On the other hand, at $U = 24$, the RKKY interaction enhances the spin-polarization and induces a spin-selective gap for the majority-spin electrons. This gap results from a co-operation of the RKKY interaction and the Kondo effect, and the gap size is indeed of the order of the Kondo temperature. The mechanism of forming the spin-selective gap is identical to the topologically trivial heavy-fermion systems;^{25–28} the gap formation leads to a commensurability condition for the majority-spin electrons, which in turn energetically stabilizes this insulating state in a metallic phase.²⁶ Note that as seen in Fig. 2, excessive interaction strength ($U = 36$) suppresses the Kondo effect and destroys the gap.

The remarkable feature of this spin-selective insulating phase is its topological structure, which emerges away from half filling, where one usually does not expect any topological phase. The topological structure can be detected via the Chern number for the majority-spin state. The corresponding topological invariant is described in terms of the Green's function as follows:^{42,43}

$$N_{\sigma} = \frac{\epsilon^{\mu\nu\rho}}{24\pi^2} \int d^3p \text{ptr} [\hat{G}_{\sigma}(p)^{-1} \frac{\partial \hat{G}_{\sigma}(p)}{\partial p_{\mu}} \hat{G}_{\sigma}(p)^{-1} \frac{\partial \hat{G}_{\sigma}(p)}{\partial p_{\nu}} \hat{G}_{\sigma}(p)^{-1} \frac{\partial \hat{G}_{\sigma}(p)}{\partial p_{\rho}}].$$

Here, the notation $p = (i\omega, \mathbf{p})$ is used. As long as the Green's function has neither gap-closing nor zero, this quantity can be simplified as⁴⁴

$$N_{\sigma}^{ch} = \frac{1}{4\pi} \int d^2k \hat{d}(k) \cdot \partial_{k_x} \hat{d}(k) \times \partial_{k_y} \hat{d}(k)$$

$$\hat{h}'_{\sigma}(k) = \mathbb{I}d_{0,\sigma}(k) + \sum_i d_i(k) \hat{\sigma}_i,$$

where $\hat{h}'_{\sigma}(k) = \hat{h}_{\sigma}(k) + \hat{\Sigma}_{\sigma}(i\omega = 0)$, and $\hat{d}_i = d_i/|d|$. The results are plotted in Fig. 3 (a). As seen in this figure, the up-spin (majority) electrons possess the non-trivial structure, $N_{\uparrow}^{ch} = 1$. We thus end up with a spin-selective topological insulator, which is embedded in a ferromagnetic metallic phase in a low-density region of our heavy-fermion system. This topological structure is reflected in a quantized Hall conductivity for the majority spin electrons. In experiments, however, a finite but non-quantized spin-Hall conductivity may be detected




FIG. 2: (Color Online). Spectral functions ($A_{\alpha,\sigma} = -\text{Im}G_{\alpha,\sigma}^R(\omega)/\pi$) at $N_{tot} = 1.3$ for several values of interaction strength. Inset: the spectral functions around the Fermi energy $\omega = 0$. For this set of parameters, the system is in the ferromagnetic phase. Besides, at $U = 24$, the up-spin state has a bulk gap. With increasing or decreasing interaction strength, the bulk gap disappears.

due to the contribution of the gapless bulk minority spin electrons. Although the non-trivial phase is realized for the above choice of the parameters, one might wonder whether it is stabilized for other choices of the parameters. Furthermore, since the width of the spin-selective gap (Δ) is very small $\Delta \sim 0.01$ (see inset of Fig. 2), a small change in the total filling (or a small change in the chemical potential) might spoil this topological structure. Contrary to these naive expectations, the above non-trivial structure is rather robust against such changes. For example, as shown in the phase diagram (Fig. 1), we find the spin-selective topological phase for $1.2 \lesssim N_{tot} \lesssim 1.4$ at $U = 24$. The corresponding changes in the electron number and the chemical potential are plotted in Figs. 3 (b) and (c) at $U = 24$. With increasing electron number from $N_{tot} = 1.2$, the chemical potential changes from -2.91 to -1.96 (Fig. 3(b)). However, the change in electron number happens only through the down-spin (minority) electrons (Fig. 3(c)).

This confirms that the spin-selective insulating behavior holds over a wide range of the chemical potential, which is about a hundred times larger than the gap size (order of the Kondo temperature), due to the cooperation of the RKKY interaction and the Kondo effect.

Systematically performing similar calculations, we finally arrive at the phase diagram already shown in Fig. 1, where a topologically non-trivial spin-selective insulator hidden in a ferromagnetic metallic phase is realized in a wide range of parameters.




FIG. 3: (Color Online). (a) Chern number for up-spin (majority) electrons. (b) chemical potential as a function of the total filling, (c) filling of each state as a function of the total filling

Edge states- Now, let us turn to the edge properties. If the Green's function does not have zeros at the boundary, the non-trivial topological structure induces a chiral edge mode,^{43,45} which is coupled to bulk ferromagnetic fluctuations. It is well known that such a chiral edge state in quantum Hall systems is described by the chiral-Luttinger liquid. However, in our system, the properties of the edge state are drastically changed by the coupling with ferromagnetic fluctuations. In order to analyze the edge states, let us consider a semi-infinite system; we assume the spin-selective topological phase in $y > 0$ and vacuum otherwise. Here, we phenomenologically intro-

duce the following action for the edge state:

$$\begin{aligned}
S &= S_{edge} + S_c + S_{mag} \\
S_{edge} &= -\frac{1}{4\pi} \sum_{n, k_x} \phi(i\omega_n, k_x) k_x (i\omega_n - vk_x) \phi(-i\omega_n, -k_x) \\
S_c &= -g \sum_{n, \mathbf{k}} ik_x \phi(i\omega_n, k_x) \psi(-i\omega_n, -\mathbf{k}) \\
S_{mag} &= \sum_{n, \mathbf{k}} \psi(i\omega_n, \mathbf{k}) \chi'^{-1}(i\omega_n, \mathbf{k}) \psi(-i\omega_n, -\mathbf{k}) \\
\chi'(i\omega_n, \mathbf{k}) &= \frac{1}{\xi^{-2} + (k_x^2 + k_y^2) + |\omega_n|/(\Gamma \sqrt{k_x^2 + k_y^2})},
\end{aligned} \tag{2}$$

where S_{edge} , S_{mag} and S_c describe the Tomonaga-Luttinger liquid for the edge state, the bulk magnetic fluctuation and the coupling between them. $\phi(k)$ describes the boson field for the edge state, and the boson field ψ describes the bulk spin fluctuations. ξ is the correlation length for the magnetic fluctuations, and Γ is a constant parameter. By integrating out the ψ field and using the relation $n_{k_x} \sim ik_x \phi(k_x)$, we obtain the two-particle Green's function ($G(x, \tau) = -\langle Tn(x, \tau)n(0) \rangle$). The retarded Green's function can be written as

$$G^R(\omega, k_x) = \frac{2\pi k_x^2}{k_x(\omega + i\delta - vk_x) + \pi g^2 k_x^2 \sum_{k_y} \chi'(k)^R}, \tag{3}$$

where $(\chi'^R(\omega, \mathbf{k}))^{-1} = \xi^{-2} + (k_x^2 + k_y^2) - i\omega/(\Gamma \sqrt{k_x^2 + k_y^2})$. From this we can conclude that the edge states show a non-Tomonaga-Luttinger liquid behavior. The dynamics shows a dissipative behavior because of the coupling with the bulk magnetic fluctuations. This implies that a composite collective magnetic mode, composed of the chiral Luttinger liquid and the spin fluctuation, emerges due to correlation effects. To characterize the anomalous dynamics, we here consider the spin-lattice relaxation time of the edge mode. Let us assume that a magnetic field is applied perpendicular to the z -axis. Then, the longitudinal NMR relaxation time (T_1) is given as,

$$\begin{aligned}
\frac{1}{T_1 T} &= CA^2 \lim_{\omega \rightarrow 0} \sum_{k_x} \frac{1}{\omega} \text{Im} \chi^{zz}(k_x, \omega + i\delta) \\
&\sim \frac{CA^2 2\pi^2 g^2}{\xi^{-4} v'^2},
\end{aligned} \tag{4}$$

where C , A and v' denote a constant including the nuclear magnetic ratio, the hyperfine coupling constant,

and the renormalized velocity, respectively. Here, we have used the relation, $\chi^{zz}(k_x, \omega + i\delta) \sim -G^R(k_x, \omega)$. From these results, we find that the relaxation time decreases when the system approaches the ferromagnetic transition point ($T_{\text{Curie}} = 0$). Moreover, according to the self-consistent renormalization (SCR) analysis,⁴⁶ the contribution of the bulk ferromagnetic fluctuations in the two-dimensional system is $1/(T_1 T) \sim \xi^3$, and the temperature dependence of correlation length is $\xi^{-2} \sim T^{2/3} e^{-4bT}$. Here, b is constant which is proportional to square of the ferromagnetic moment at $T = 0$. Therefore, if the magnetic fluctuations become stronger, the edge contribution becomes dominant and is experimentally observable; near the transition point ($T = 0$), edge and bulk contributions are $1/(T_1 T) \sim T^{-4/3} e^{8bT}$ and $1/(T_1 T) \sim T^{-1} e^{6bT}$, respectively.

Summary- We have proposed a spin-selective topological insulator in a two-dimensional heavy-fermion system, which is realized in a ferromagnetic metallic phase. In this phase, a spin-selective gap is formed only in the majority-spin state, providing a topological insulating behavior. The many-body nature due to the RKKY interaction and the Kondo effect supports the robustness of the topological phase against a change in the chemical potential in a much larger range than the spin-selective gap. We have shown that the bulk topological structure gives the quantized Hall conductivity for the majority-spin electrons, thereby supporting the existence of a topologically protected chiral edge state. We have also discussed the effect of the bulk ferromagnetic fluctuations on the edge mode; the spin correlation function exhibits a non-Tomonaga-Luttinger liquid behavior with a large damping coming from bulk ferromagnetic fluctuations which may be detected by the NMR measurement. So far, topological Kondo insulators are proposed for some heavy-fermion compounds²⁹⁻³¹, which may be described by the half-filled Kondo lattice model. If holes could be doped into such topological insulators, we may have a chance to realize a spin-selective topological insulator even in a metallic phase.

Acknowledgments- This work is partly supported by JSPS through its FIRST Program, KAKENHI (Nos. 20102008, 23102714, 23540406), and the Global COE Program "The Next Generation of Physics, Spun from Universality and Emergence" from MEXT of Japan. T. Y. thanks the Japan Society for the Promotion of Science (JSPS) for Research Fellowships for Young Scientists.

¹ M. Z. Hassan and C. L. Kane, Rev. Mod. Phys. **82** 3045-3067 (2010).

² X. L. Qi and S. C. Zhang, Rev. Mod. Phys. **83**, 1057 (2011).

³ M. König, S. Wiedmann, C. Brüne, A. Roth, H. Buhmann,

L. W. Molenkamp, X. L. Qi, and S. C. Zhang, Science **318** 776 (2007).

⁴ D. Hsieh, D. Qian, L. Wray, Y. Xia, Y. S. Hor, R. J. Cava, and M. Z. Hassan, Nature **452** 970 (2008).

- ⁵ Y. Xia, D. Qian, D. Hsieh, L. Wray, A. Pal, H. Lin, A. Bansil, D. Grauer, Y. S. Hor, R. J. Cava, and M. Z. Hassan, *Nat. Phys.* **5** 398 (2009).
- ⁶ Y. L. Chen, J. G. Analytis, J.-H. Chu, Z. K. Liu, S.-K. Mo, X. L. Qi, H. J. Zhang, D. H. Lu, X. Dai, Z. Fang, S. C. Zhang, I. R. Fisher, Z. Hussain, and Z.-X. Shen, *Science* **325** 178 (2009).
- ⁷ A. Shitade, H. Katsura, J. Kunes, X.-L. Qi, S. C. Zhang, and N. Nagaosa, *Phys. Rev. Lett.* **102** 256403 (2009).
- ⁸ D. A. Pesin and L. Balents, *Nature Physics* **6**, 376 - 381 (2010) .
- ⁹ S. Chadov, X.-L. Qi, J. Kubler, G. H. Fecher, C. Felser, and S.-C. Zhang, *Nature Materials* **9**, 541-545 (2010).
- ¹⁰ H. Lin, L. A. Wray, Y. Xia, S. Xu, S. Jia, R. J. Cava, A. Bansil, and M. Z. Hasan, *Nature Materials* **9**, 546-549 (2010).
- ¹¹ B. Yan, L. Muchler, X.-L. Qi, S.-C. Zhang, and C. Felser, *Phys. Rev. B* **85**, 165125 (2012).
- ¹² Y. Yamaji and M. Imada, *Phys. Rev. B* **83** 205122 (2011).
- ¹³ M. Hohenadler, T. C. Lang, and F. F. Assaad, *Phys. Rev. Lett.* **106** 100403 (2011).
- ¹⁴ D. Zheng, C. Wu, and G.-M. Zhang, *arXiv: 1011.5858v2* (2010).
- ¹⁵ S. L. Yu, X. C. Xie, and J. X. Li, *Phys. Rev. Lett.* **107** 010401 (2011).
- ¹⁶ W. Wu , S. Rachel, W.-M. Liu, and K. L. Hur, *arXiv:1106.0943v1*. (2011)
- ¹⁷ S. Rachel and K. LeHur, *Phys. Rev. B* **82** 075106 (2010).
- ¹⁸ C. N. Varney, K. Sun, M. Rigol, and V. Galitski, *Phys. Rev. B* **82** 115125 (2010).
- ¹⁹ L. Wang, H. Shi, S. Zhang, X. Wang, X. Dai and X. C. Xie, *arXiv. 1012.5163v1* (2011).
- ²⁰ T. Yoshida, S. Fujimoto, and N. Kawakami, *Phys. Rev. B* **85**, 125113 (2012).
- ²¹ Y. Tada, R. Peters, M. Oshikawa, A. Koga, N. Kawakami, and S. Fujimoto, *Phys. Rev. B* **85**, 165138 (2012).
- ²² S. Raghu, X.-L. Qi, C. Honerkamp, and S. C. Zhang, *Phys. Rev. Lett.* **100** 156401 (2008).
- ²³ Y. Zhang, Y. Ran, and A. Vishwanath, *Phys. Rev. B* **79** 245331 (2009).
- ²⁴ M. Kurita, Y. Yamaji, and M. Imada, *J. Phys. Soc. Jpn.* **80** 044708 (2011).
- ²⁵ K. S. D. Beach and F. F. Assaad, *Phys. Rev. B* **77** 205123 (2008).
- ²⁶ R. Peters, N. Kawakami, and Th. Pruschke, *Phys. Rev. Lett.* **108** 086402 (2012).
- ²⁷ O. Howczak, and J. Spalek, *J. Phys.: Condens. Matter* **24** 205602 (2012).
- ²⁸ R. Peters and N. Kawakami, *Phys. Rev. B* **86** 165107 (2012).
- ²⁹ M. Dzero, K. Sun, V. Galitski, P. Coleman, *Phys. Rev. Lett.* **104** 106408 (2010).
- ³⁰ M. Dzero, K. Sun, P. Coleman, and V. Galitski, *Phys. Rev. B* **85** 045130 (2012).
- ³¹ M.-T. Tran, T. Takimoto, and K.-S. Kim, *Phys. Rev. B* **85** 125128 (2012).
- ³² T. Takimoto, *J. Phys. Soc. Jpn* **80** 123710 (2011).
- ³³ F. Lu, J. Zhao, H. Weng, Z. Fang, and X. Dai, *arXiv:1211.5863*
- ³⁴ J. Botimer, D.J. Kim, S. Thomas, T. Grant, Z. Fisk, and J. Xia, *arXiv:1211.6769*
- ³⁵ X. Zhang, N. P. Butch, P. Syers, S. Ziemak, R. L. Greene, and J. Paglione, *arXiv:1211.5532*
- ³⁶ B. A. Bernevig, T. L. Hughes, and S. C. Zhang, *Science* **314** 1757 (2006).
- ³⁷ A. Georges, G. Kotliar, W. Krauth and M. J. Rozenberg, *Rev. Mod. Phys.* **68** 13-125 (1996).
- ³⁸ W. Metzner and D. Vollhardt, *Phys. Rev. Lett.* **62** 324 (1989).
- ³⁹ E. M. Hartmann, *Z. Phys. B Condens. Matter* **74** 507 (1989).
- ⁴⁰ K. Wilson, *Rev. Mod. Phys.* **47**, 773 (1975).
- ⁴¹ R. Bulla, T. Costi, and T. Pruschke, *Rev. Mod. Phys.* **80**, 395 (2008).
- ⁴² G. E. Volovik, *The Universe in a Helium Droplet* (Oxford, 2003).
- ⁴³ V. Gurarie, *Phys. Rev. B* **83** 085426 (2011).
- ⁴⁴ Z. Wang and S. C. Zhang, *Phys. Rev. X* **2** 031008 (2012).
- ⁴⁵ A. M. Essin and V. Gurarie, *Phys. Rev. B* **84** 125132 (2011).
- ⁴⁶ M. Hatatani and T. Moriya *J. Phys. Soc. Jpn.* **64** 3434 (1995).